

AGEPAN[®] SYSTEM – THE RIGHT CHOICE WHEN IT COMES TO FIRE PROTECTION AND SOUND INSULATION!








FIRE PROTECTION FOR A SAFE HOME!

Structural fire protection is indispensable in modern timber frame construction, as safety is the top priority. AGEPAN[®] SYSTEM superstructures can also be relied on in this area.

Applied in the system - our constructions have passed the fire protection tests. Based on the fire resistance tests carried out at MFPA Leipzig GmbH (Institute for Materials Research and Testing for the Construction Industry), we have successfully verified load-bearing, space-enclosing timber stud wall constructions according to DIN 4102-2 (1977-09) and DIN EN 13501-2 (2010-2).

- Comprehensively tested fire protection system structures
- Exceptional strength
- Load-bearing

FIRE PROTECTION EXAMPLES OF TESTED STRUCTURES

	STRUCTURE	PRODUCT	THICKNESS [mm]
 <p>P-SAC-02-III-712 F 60-B (REI 60)</p>	INTERIOR	Gypsum board	≥ 12,5
		AGEPAN® THD Install	≥ 40
		AGEPAN® OSB 3 Ecoboard®	≥ 15
	EXTERIOR	Solid structural timber	≥ 60 x 140
		Mineral wool (rockwool)	≥ 140
		AGEPAN® DWD protect	16
 <p>P-SAC-02-III-712 F 60-B (REI 60)</p>	INTERIOR	Gypsum board	≥ 12,5
		AGEPAN® THD Install	≥ 40
		AGEPAN® OSB 3 Ecoboard®	≥ 15
	EXTERIOR	Solid structural timber	≥ 60 x 140
		Mineral wool (rockwool)	≥ 140
		AGEPAN® UDP T+G	≥ 22
 <p>P-SAC-02-III-713 F 90-B (REI 90)</p>	INTERIOR	Gypsum board	≥ 12,5
		AGEPAN® THD Install	≥ 40
		AGEPAN® OSB 3 Ecoboard®	≥ 15
	EXTERIOR	Solid structural timber	≥ 60 x 140
		Mineral wool (rockwool)	≥ 140
		AGEPAN® THD Putz 050	≥ 40
 <p>P-SAC-02-III-1112 F 30-B (REI 90*)</p>	INTERIOR	Gypsum board	≥ 12,5
		AGEPAN® THD Install	≥ 60
		AGEPAN® OSB 3 Ecoboard®	≥ 15
	EXTERIOR	Solid structural timber	≥ 60 x 200
		Cellulose (Isocell)	≥ 200
		AGEPAN® THD T+G	≥ 60
 <p>P-SAC-02-III-1110 F 30-B (REI 30*)</p>	INTERIOR	AGEPAN® OSB 3 Ecoboard®	≥ 15
		Solid structural timber	≥ 60 x 200
	EXTERIOR	Cellulose (Isocell)	≥ 200
		AGEPAN® DWD protect	16

Test certificates will be provided to you on request.

* Classification DIN EN 13501-2:2016-12







SOUND INSULATION FOR A QUIET HOME!

When it comes to sound insulation, we have plenty to offer as well. Noise pollution can be significantly reduced by our system constructions. The efficient use of tested system structures helps to achieve an excellent sound insulation and provides a pleasantly quiet home.

- Tested sound insulating system structures according to DIN EN ISO 10140-2 in accordance with requirements to DIN 4109
- Exceptional sound insulating properties due to the asymmetrical THD bulk density profile
- Effective sound insulation due to an absorbing fibre structure

SOUND INSULATION EXAMPLES OF TESTED STRUCTURES

	STRUCTURE	PRODUCT	THICKNESS [mm]
 <p>Exterior wall $R_{w,p} = 50$ dB F 90-B (REI 90)</p>	INTERIOR	Gypsum board	≥ 12,5
		AGEPAN® THD Install	≥ 60
		AGEPAN® OSB 3 Ecoboard®	≥ 15
		Solid structural timber	≥ 60 x 140
		Mineral wool (rockwool)	≥ 140
		AGEPAN® THD Putz 050	≥ 40
 <p>P-SAC 02/IV/17-013-2 Roof – new build $R_{w,p} = 50$ dB</p>	INTERIOR	Gypsum board	≥ 12,5
		AGEPAN® OSB 3 Ecoboard®	≥ 15
		Rafters (solid structural timber)	≥ 80 x 200
		Cellulose (Isocell)	≥ 200
		AGEPAN® THD T+G	≥ 80
		Support and counter battens	≥ 60 x 40
 <p>P-SAC 02/IV/17-013-3 Roof – renovation $R_{w,p} = 49$ dB</p>	INTERIOR	Gypsum board	≥ 12,5
		AGEPAN® THD Install	≥ 60
		AGEPAN® OSB 3 Ecoboard®	≥ 15
		Rafters (solid structural timber)	≥ 100 x 160
		Cellulose (Isocell)	≥ 160
		AGEPAN® THD T+G	≥ 80
 <p>P-SAC 02/IV/17-013-3 Roof – renovation $R_{w,p} = 49$ dB</p>	EXTERIOR	Support and counter battens	≥ 60 x 40
		Roof tiles	

Test certificates will be provided to you on request.